



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 067 234 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

10.01.2001 Bulletin 2001/02

(51) Int. Cl.⁷: **D06N 3/00**

(21) Application number: **00114045.8**

(22) Date of filing: **05.07.2000**

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

Designated Extension States:

AL LT LV MK RO SI

(30) Priority: **05.07.1999 JP 19023499**

(71) Applicant: **KURARAY CO., LTD.**

Kurashiki-shi, Okayama-ken 710 (JP)

(72) Inventors:

- Nakayama, Kimio
Kurashiki-shi, Okayama-ken (JP)
- Yamasaki, Tsuyoshi
Kurashiki-shi, Okayama-ken (JP)
- Tamba, Yoshihiro
Kurashiki-shi, Okayama-ken (JP)

(74) Representative:

**VOSSIUS & PARTNER
Siebertstrasse 4
81675 München (DE)**

(54) **Fibrous substrate for artificial leather and artificial leather using the same**

(57) A fibrous substrate for artificial leather, comprising microfine fiber bundles, each of which is composed of 3-50 microfine fibers (A) comprising an elastic polymer and having an average fineness of 0.5 denier or less and 15 or more microfine fibers (B) comprising a non-elastic polymer and having an average fineness of 0.2 denier or less, the microfine fiber bundles satisfying the following conditions (1)-(3):

(1) the ratio of the number of strands of the A to the number of strands of the B in cross sections of the bundles (A/B) is 1/5 or less,

(2) the ratio of the weight of the A to the weight of the B in the bundles (A/B) is 10/90-60/40, and

(3) the microfine fibers (B) comprising the non-elastic polymer encircle each of the microfine fibers (A) comprising the elastic polymer.

It is possible to obtain, from the fibrous substrate, suede-like artificial leather and grain-like artificial leather having texture and appearance like natural leather, and having high-class feeling never available from artificial leather in the prior art.

EP 1 067 234 A2

BEST AVAILABLE COPY

Description

[0001] The present invention relates to a fibrous substrate for artificial leather that has less rubbery feeling and repellence feeling than conventional artificial leather, is excellent in denseness feeling and has texture like soft natural leather.

[0002] At present, artificial leather is generally produced by a method which comprises impregnating a nonwoven fabric comprising fibers (referred to as microfine fiber-forming fibers) which are composed of a non-elastic polymer such as nylon or polyester and come to generate microfine fibers with a solution of an elastic polymer, mainly polyurethane, in an amount of 15-60% by weight of the nonwoven fabric, solidifying the elastic polymer by a wet process or a dry process, and then generating bundles of microfine fibers from the microfine fiber-forming fibers, or the like method. According to this method, the elastic polymer with which the fabric is impregnated is solidified into a sponge or block form to make a structure wherein the solidified elastic polymer covers and encircles the microfine fiber bundles. Therefore, the resultant artificial leather has strong rubbery feeling and repellence feeling that are peculiar to the elastic polymer, and is inferior to natural leather in feeling performances such as texture, drapeability, and denseness feeling and surface feeling of the surface. Since the elastic polymer is used in a solvent system, production steps such as solvent-recovery are complicated so that productivity is bad. In many cases, the solvent is harmful for human bodies. Thus, the above-mentioned method is involved in environmental problems upon the production.

[0003] Incidentally, natural leather is composed only of fibers and has a structure wherein several hundreds of very fine microfibrils of collagen are bundled into a fiber (about 0.05-1.0 denier); from several fibers to several tens of the fibers are made up to a fiber bundle (1-10 deniers); and microfibrils, fibers or fiber bundles are three-dimensionally and densely entangled with each other. For artificial leather, there are also suggested many trials for obtaining texture, denseness feeling and appearance that are very similar to those peculiar to natural leather, using a fibrous substrate composed only of fibers wherein a fibrous elastic polymer is used as a binder.

[0004] For example, JP-A-59-211664, 59-211666, 60-45656, 60-139879, 63-12744, 64-52872 and 2-14056 disclose methods for producing a leather-like sheet by blending sea-island type microfine fiber-forming fibers whose island component is an elastic polymer with non-elastic fibers to prepare a nonwoven fabric, and then removing the sea component of the sea-island type microfine fiber-forming fibers to generate elastic microfine fibers. In these methods, pieces of the elastic polymer, which is the island component, agglutinate to each other to be bundled/integrated by treatment with the solvent upon extraction and removal of the sea component, even if the microfibers comprising the elastic polymer are made sufficiently fine at the stage of the microfine fiber-forming fibers. Finally, a single thick fiber is produced. For this reason, the fineness of the elastic polymer that can be industrially produced exceeds 2 deniers. The elastic polymer and the non-elastic polymer are separately made into fiber bundles, so that only a part of the microfine fibers comprising the non-elastic polymer is bound with the elastic polymer. Thus, large parts of fibers comprising the non-elastic polymer are in a loose state. As a result, many of the microfine fibers are not bound and easily fall out from the leather-like sheet.

[0005] As examples of the fiber form in which an elastic polymer and a non-elastic polymer coexist in a single fiber bundle, JP-A-61-194247 and 10-37057 disclose methods using core-sheath type composite fibers wherein its core component is an elastic polymer and its sheath component is a blend polymer in which a non-elastic polymer is dispersed in an island form in a sea component comprising a soluble polymer. JP-A- 5-339863 and 5-339864 disclose methods using composite fibers wherein a soluble polymer in which an elastic polymer is dispersed in an island form and a soluble polymer in which a non-elastic polymer is dispersed in an island form are put on each other side-by-side. According to the former methods, the non-elastic polymer can be made into microfibers. However, the number of strands of the fiber comprising the elastic polymer is only one; therefore, the fineness of the elastic polymer that can be industrially produced is a large value over 1 denier. According to the latter methods, upon dissolution/removal of the soluble component, the elastic polymer agglutinates into thick fibers so that the fibers have strong repellence feeling and rubbery feeling. Thus, no artificial leather like natural leather can be obtained.

[0006] As described above, in all of the above-mentioned methods, the fineness of fibers comprising elastic polymer exceeds 1 denier and is too large as compared with natural leather. Therefore, no texture like natural leather can be obtained, and the denseness and smoothness of their surface are poor.

[0007] Examples using composite fibers wherein an elastic polymer and a non-elastic polymer are divided are disclosed in JP-A- 62-41375, 62-78246, 2-160964 and 6-173173. According to these methods, the industrial limits of both the fineness of fibers comprising the non-elastic polymer and that of fibers comprising the elastic polymer are about 0.5 denier. The fineness of both the obtained non-elastic fibers and elastic fibers is larger than that of natural leather. Texture like natural leather cannot be expected.

[0008] According to all of the methods, which have been disclosed up to the present, using an elastic polymer in a fiber form, the fineness of the elastic polymer is far larger than that of natural leather. As a result, texture and appearance are far and away from those of natural leather.

[0009] As described above, any elastic polymer cannot be made into microfibers according to the prior art, so that

texture and appearance like natural leather cannot be gained. An object of the present invention is to attain conversion of an elastic polymer into microfibrils and provide a fibrous substrate for artificial leather which has less rubbery feeling and repellence feeling than artificial leather in the prior art, has denseness feeling, and has texture and appearance like soft natural leather.

[0010] In order to obtain artificial leather having texture and appearance like natural leather, investigations were made on methods by which an elastic polymer as an island component is made into microfibrils without agglutination/integration of pieces of the polymer even if a sea component is extracted and removed with e.g. a solvent. If microfibrils (A) comprising an elastic polymer are adjacent to each other, they agglutinate to each other and are integrated into bundles upon the extraction and removal. Upon the extraction and removal, however, microfibrils (B) comprising a non-elastic polymer do not agglutinate to each other. A hint was obtained from this fact. Thus, a method was tried wherein the microfibrils (B) comprising the non-elastic polymer encircle the microfibrils (A) comprising the elastic polymer for preventing the phenomenon that pieces of the elastic polymer are integrated into bundles. From microfibril-forming fibers wherein many microfibrils (B) comprising the elastic polymer are substantially homogeneously dispersed in a sea component polymer containing many of the dispersed microfibrils (A) comprising the elastic polymer, the sea component polymer is extracted and removed by a solvent. As a result, the elastic polymer is separated into microfibrils, so as to form microfibril bundles wherein the microfibrils (A) comprising the elastic polymer and the microfibrils (B) comprising the non-elastic polymer are blended and integrated with each other. In the resultant microfibril fibrous substrate, the microfibrils (B) comprising the non-elastic polymer cover and encircle the microfibrils (A) comprising the elastic polymer, so as to make a fine entanglement structure, like natural leather, wherein the microfibrils (B) comprising the non-elastic polymer near the microfibrils (A) comprising the elastic polymer agglutinate to the microfibrils (A). Thus, the substrate has texture and appearance like natural leather. As described above, the fact has been confirmed that by making an elastic polymer into microfibrils, a dense and microfibril fiber substrate like natural leather is made to give a leather-like sheet having texture and appearance like natural leather. Thus, the present invention has been made.

[0011] The present invention relates to a fibrous substrate for artificial leather, comprising microfibril fiber bundles, each of which is composed of 3-50 numbers of microfibrils (A) comprising an elastic polymer and having an average fineness of 0.5 denier or less and 15 or more numbers of microfibrils (B) comprising a non-elastic polymer and having an average fineness of 0.2 denier or less, the microfibril fiber bundles satisfying the following conditions (1)-(3):

- (1) the ratio of the number of strands of the A to the number of strands of the B in cross sections of the bundles (A/B) is 1/5 or less,
- (2) the ratio of the weight of the A to the weight of the B in the bundles (A/B) is 10/90-60/40, and
- (3) the microfibrils (B) comprising the non-elastic polymer encircle each of the microfibrils (A) comprising the elastic polymer.

[0012] The leather-like sheet of the present invention can be obtained by performing the following steps (a)-(d):

the step (a) of producing microfibril fiber-forming fibers that can be converted into microfibril fiber bundles as described above,

the step (b) of producing a fiber-entangled nonwoven fabric comprising the fibers,

the step (c) of removing a sea component polymer constituting the fibers to convert the fibers into microfibril fiber bundles comprising microfibrils (A) comprising an elastic polymer (A) [hereinafter referred to as elastic microfibrils (A)] and microfibrils (B) comprising a non-elastic polymer (B) [hereinafter referred to as non-elastic microfibrils (B)], and

the step (d) of napping at least one surface of the resultant fiber bundled and dyeing the resultant fiber-napped sheet, or of applying a resin layer that will make a grain-like surface to at least one surface of the resultant fiber bundles.

[0013] In order to obtain artificial leather having high-class feeling such as texture and softness like natural leather and surface-denseness feeling, first, it is essential for the present invention that fibers comprising a non-elastic polymer is finer than fibers comprising an elastic polymer. In order to prevent agglutination and integration of fibers comprising an elastic polymer, it is essential for the present invention that fine fibers around the elastic polymer fibers are composed of a non-elastic polymer.

[0014] It is necessary for the present invention that the microfibril fiber-forming fibers are in the following state: fibers comprising an elastic polymer and fibers comprising a non-elastic polymer are blended and integrated with each other in the sea component polymer and further the fibers comprising the elastic polymer and the fibers comprising the non-elastic polymer are substantially homogeneously dispersed in the whole of fiber cross sections without uneven distribution. That is, in side-by-side type fibers, wherein fibers comprising an elastic polymer and fibers comprising a non-elas-

tic polymer are subjected to extremely uneven distribution, or the like fibers, the non-elastic microfibrillar fibers (B) cannot sufficiently encircle the elastic microfibrillar fibers (A) so that the pieces of the elastic polymer agglutinate strongly to each other in the microfibrillar fiber-making step. As a result, microfibrillar fibers cannot be obtained. Thus, these fibers are not preferred in the present invention.

5 [0015] Such-microfibrillar fiber-forming fibers can be obtained as follows:

- 1) a spinning method comprising blending the non-elastic polymer constituting the non-elastic microfibrillar fibers (B) with the sea component polymer at a prescribed blend ratio, melting the blend in a single melting system, and causing this to flow together with the elastic polymer constituting the elastic microfibrillar fibers (A) melted in another system, with the fiber shape being defined through a spinneret portion,
- 10 2) a spinning method comprising blending the elastic polymer constituting the elastic microfibrillar fibers (A) with the sea component polymer at a prescribed blend ratio, melting the blend in a single melting system, and causing this to flow together with the non-elastic polymer constituting the non-elastic microfibrillar fibers (B) melted in another system, with the fiber shape being defined through a spinneret portion,
- 15 3) a spinning method comprising blending the non-elastic polymer constituting the non-elastic microfibrillar fibers (B) with the sea component polymer at a prescribed blend ratio, melting the blend in a single melting system, blending the elastic polymer constituting the elastic microfibrillar fibers (A) melted in another system with the sea component polymer at a prescribed ratio, melting the blend in a single melting system, and causing these to flow into each other with the fiber shape being defined through a spinneret portion,
- 20 4) a spinning method comprising repeating joint-division plural times at a spinning head portion to form a blend system of the two instead of the spinning manner of defining the fiber shape through the spinneret portion in the above-mentioned methods, or the like spinning method. Among these methods, the above-mentioned method 1) or method 4) is preferred since the microfibrillar fiber-forming fibers defined in the present invention can easily be obtained.

25 [0016] In order to produce microfibrillar fibers without agglutination and integration of pieces of the elastic polymer upon extraction and removal of the sea component polymer with e.g. a solvent, it is necessary in the present invention that the microfibrillar fiber-forming fibers are produced to have a structure in which the number of strands of the elastic microfibrillar fibers (A) is 3-50 and the number of strands of the non-elastic microfibrillar fibers (B) is 15 or more in any cross section along the direction perpendicular to the fiber axis of any one of the microfibrillar fiber bundles, the ratio of the numbers of strands (A/B) is 1/5 or less, and the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B) are blended and integrated in the microfibrillar fiber bundles. The structure wherein the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B) are blended and integrated means a state in which the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B) are substantially dispersed in the whole of any cross section of the bundle without locally uneven distribution.

35 [0017] When the number of strands of the elastic microfibrillar fibers (A) is over 50, the elastic microfibrillar fibers (A) are too close to each other so that the elastic microfibrillar fibers (A) agglutinate to each other and are integrated upon the extraction and removal of the sea component to make a structure wherein the non-elastic microfibrillar fibers are also taken therein. As a result, the structure becomes too dense so that its texture is hard and mechanical properties such as tear strength deteriorate. On the other hand, if the number of strands of the elastic polymer fibers is below 3, the average fineness of the elastic polymer exceeds 1 denier so that surface denseness and smoothness deteriorate. Besides, the elastic polymer having a large fineness is bared to the surface of the substrate. Because of high frictional resistance thereof, rough-surface feeling becomes strong. When this is used for dyed articles, color spots of the elastic polymer against the non-elastic polymer become conspicuous so that its appearance deteriorates. When the weight proportion of the elastic polymer is lowered, the average fineness of the elastic polymer can be lowered. In this case, however, the resultant artificial leather is like dish cloth and has poor texture. Preferably, the number of strands of the elastic polymer fibers is 5-45.

40 [0018] When the number of strands of the non-elastic microfibrillar fibers (B) is below 15, the shield of the elastic microfibrillar fibers (A) is insufficient. Thus, the elastic microfibrillar fibers (A) agglutinate to each other and are integrated upon the extraction and removal of the sea component to make a structure wherein the non-elastic microfibrillar fibers are also taken therein. Besides the content by percentage of the non-elastic polymer is preferably about 50% or more in the light of the process and practical use. Therefore, the fineness of the non-elastic polymer that can be industrially produced is as large as about 0.2 denier or more. As a result, the resultant product has hard texture and poor mechanical properties such as tear strength. The number of the non-elastic microfibrillar fibers (B) is 15 or more, preferably 25 or more, and more preferably 50 or more. The number of strands is preferably 5000 or less from the viewpoint of production easiness.

55 [0019] When the ratio of the number of strands of the elastic microfibrillar fibers (A) to that of the non-elastic microfibrillar fibers (B) (A/B) is over 1/5, the non-elastic microfibrillar fibers (B) cannot sufficiently encircle the elastic microfibrillar fibers (A).

Thus, the elastic microfibrils (A) agglutinate to each other and are integrated upon the extraction and removal of the sea component to make a structure wherein the non-elastic microfibrils are also taken therein. As a result, the structure becomes too dense so that its texture is hard and mechanical properties such as tear strength deteriorate. The ratio between the above-mentioned numbers of strands (A/B) is preferably 1/10 or less. The ratio is preferably 1/2000 or more from the viewpoint of production easiness. The ratio of the average fineness of the elastic microfibrils (A) to that of the non-elastic microfibrils (B) (A/B) is preferably in the range of 2 to 5000 and more preferably from 5 to 500 from the viewpoint of easy attainment of the object of the present invention and easiness of fiber production.

[0020] It is necessary that the weight ratio of the A to the B (A/B) in the microfibril fiber bundles ranges from 10/90 to 60/40. When the proportion of the A is over 60/40, practical performances such as mechanical properties do not reach a sufficient level. Besides, the repellence feeling and rubbery feeling that are peculiar to the elastic polymer become strong. Moreover, the elastic microfibrils (A) are too close to each other so that the elastic microfibrils (A) agglutinate to each other and are integrated upon the extraction and removal of the sea component to make a structure wherein the non-elastic microfibrils are also taken therein. Consequently, the resultant product has hard texture, and has rubbery feeling and repellence feeling. Thus, practical performances deteriorate. Conversely, when the weight ratio (A/B) is below 10/90, the elastic polymer is made into microfibrils. However, part of the non-elastic microfibrils (B) that are not close to the elastic microfibrils (A) increases so that the amount of the non-elastic microfibrils (B) which do not bind the elastic microfibrils (A) increases. Thus, the resultant structure becomes loose so that texture like natural leather cannot be obtained. Besides, the fibers come to have pores. Thus, problems about the process or practical use arise. The weight ratio (A/B) is preferably in the range of 15/85 to 55/45.

[0021] When the average fineness of the elastic microfibrils (A) is over 0.5 denier, the repellence feeling peculiar to the elastic polymer is raised. Further, surface denseness and smoothness deteriorate. Thus, it is difficult that the resultant keeps texture and appearance like natural leather. The average fineness of the elastic microfibrils (A) is preferably 0.3 denier or less, and more preferably 0.2 denier or less, and is preferably 0.005 denier or more. When the average fineness of the non-elastic microfibrils (B) is over 0.2 denier, the resultant product has hard texture. Besides, problems about surface denseness and smoothness arise. Thus, it is difficult that the resultant keeps texture and appearance like natural leather. The average fineness of the non-elastic microfibrils (B) is preferably 0.15 denier or less, and more preferably 0.1 denier or less, and is preferably 0.0002 denier or more.

[0022] In the microfibril fiber-forming fibers of the present invention, the elastic polymer constituting the elastic microfibrils (A) as an island component means any polymer whose elongation recovery ratio at the time of 1 minute after the polymer is elongated by 50% at room temperature is 50% or more. The non-elastic polymer means any polymer whose elongation recovery ratio measured in the same manner for the non-elastic polymer is 50% or less, or any polymer whose limit elongation ratio does not reach 50% at room temperature.

[0023] Examples of the elastic polymer include polyurethanes obtained by reacting at least one selected from polymer polyols having a number-average molecular weight of 500 to 3500, such as polyester polyols, polyether polyols, polyester ether polyols, polylactone polyols and polycarbonate polyols with an organic diisocyanate such as 4,4'-diphenylmethane diisocyanate, tolylene diisocyanate, isophorone diisocyanate, dicyclohexylmethane-4,4'-diisocyanate or hexamethylene diisocyanate and a chain extender having two active hydrogen atoms, such as 1,4-butanediol or ethylenediamine; ester-based elastomers such as polyester elastomers and polyether ester elastomers; amide-based elastomers such as polyether ester amide elastomers, polyester amide elastomers; block copolymer polymers having in the molecular thereof a conjugated diene-based polymer or a conjugated diene-based polymer block such as polyisoprene or polybutadiene; and melt-spinnable elastomers having rubber elasticity. Above all, polyurethanes are most preferable since their softness and frictional resistance are high and their repellence is low so as to produce an effect for binding non-elastic microfibrils and their heat resistance and endurance are high.

[0024] The non-elastic polymer constituting the non-elastic microfibrils (B) as the island component has a function for separating the microfibrils (A) of the elastic polymer without agglutination thereof and making them into microfibrils. Therefore, it is preferred to select a non-elastic polymer, the pieces of which do not agglutinate to each other by treatment with a solvent used for extraction and removal of the sea component. Specifically, preferable is a polymer having a solvent swelling ratio, following the treatment, of 10% or less by weight. Such a non-elastic polymer is at least one melt-spinnable polymer that is selected from melt-spinnable polyamides such as nylon-6, nylon-66, nylon-10, nylon-11, nylon-12 and copolymers thereof, melt-spinnable polyesters such as polyethylene terephthalate, polybutylene terephthalate and cation-dyeable type modified polyethylene terephthalate and melt-spinnable polyolefines such as polypropylene and copolymers thereof. Of course, two or more polymers may be mixed and used.

[0025] On the other hand, the polymer constituting the sea component (the polymer that should be extracted and removed) is a polymer whose solubility or decomposability against a solvent or a decomposing agent is different from that of the island component polymer (the polymer constituting the sea component has high solubility or decomposability), whose affinity for the island polymer is small, and whose surface tension is small or whose melt viscosity is lower than that of the island component present in the same melt system. Examples thereof include at least one melt-spinnable

ble polymer which is selected from polymers that can easily be dissolved, such as polyethylene, polystyrene, modified polystyrene and ethylene/propylene copolymers, and polymers that can easily be decomposed, such as polyethylene terephthalate modified (copolymerized) with sodium sulfoisophthalate or polyethylene glycol.

[0026] From the viewpoint of melt spinning stability, it is preferred to select a polymer having a melting point suitable for temperature at which the elastic polymer can be melt-spun as the non-elastic polymer and the polymer constituting the sea component. For example, in the case that any one of polyurethanes is used as the elastic polymer, the melting points of the non-elastic polymer and the polymer constituting the sea component are preferably about 230°C or lower. In the case that any one of polyester elastomers and polyamide elastomers is used as the elastic polymer, the melting points of the non-elastic polymer and the polymer constituting the sea component are preferably about 260°C or lower.

[0027] The fineness, the number of strands and the fiber length of the microfibrillar fibers constituting the island component of a flow of the blended polymers can be adjusted by changing e.g. the combination of the blend ratio between the non-elastic polymer or the elastic polymer constituting the flow and the sea component polymer, the melt viscosity thereof and/or the surface tension thereof. In general, if the blend ratio of the polymer constituting the island component to the sea component polymer is made high, the number of strands of the island component fibers increases. If the melt viscosity and the surface tension of the island polymer are made high, the following tendency is exhibited: the fineness increases, the number of strands of the fibers decreases, and the fiber length is shortened. On the basis of this tendency, the fineness, the number of strands and the fiber length of the non-elastic polymer or the elastic polymer, constituting the island component, of the blended-polymers-flow in the microfibrillar fiber-forming fibers can be recognized by combining appropriately the polymer constituting the island component and the polymer constituting the sea component in the blended-polymers-flow and then test-spinning the combination, according to actual spinning temperature and speed.

[0028] Finite is the length of the island component fibers in the fibers obtained from the blended-polymers-flow wherein the non-elastic polymer or the elastic polymer and the sea component polymer are blended and melted in a single melting system. However, the length is preferably 5 mm or more in order to keep mechanical properties based on entanglement with the microfibrillar fibers or the agglutination/entanglement with the non-elastic microfibrillar fibers (B) and the elastic microfibrillar fibers (A), and suppress the elongation of base cloth in the process. It is however difficult in the art to obtain microfibrillar fibers having a length of 80 cm or more by blend spinning. The fiber length of the non-elastic polymer or the elastic polymer obtained from the blended-polymers-flow can be changed at will by selecting a combination of the non-elastic polymer or the elastic polymer and the sea component polymer upon spinning. In the case that any one of polymers selected from the above-mentioned polyurethanes, polyester elastomers and polyamide elastomers is used as the constituent elastic polymer, it is possible to obtain fibers which are excellent in melt spinning stability and have a sufficiently long fiber length. Moreover, such a polymer has a large fractional resistance against the non-elastic microfibrillar fibers (B) to have a sufficient effect for fixing the fibers. Thus, such a case is optimum. In the case that blend spinning is not used but composite spinning is used, the fiber length of the resultant microfibrillar fibers is infinite. However, in the case that the microfibrillar fibers are made up to artificial leather, the fibers are usually cut to be used as staple fibers. Thus, the fiber length does not exceed the fiber length of staple fibers.

[0029] If necessary, the microfibrillar fiber-forming fibers are subjected to treatment steps such as stretching, crimping, heat setting and cutting, so as to be made into fibers having a fineness of 1 to 20 deniers. The fineness and the average fineness referred to in the present invention can easily be determined from the cross sections of the microfibrillar fiber-forming fibers. That is, a cross section of the microfibrillar fiber-forming fibers is photographed with a microscope, and then the respective number of strands of the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B) in the fiber section are counted. The respective weights of the elastic microfibrillar fiber (A) constituting a fiber of 9000 m in length and the non-elastic microfibrillar fiber (B) constituting the same fiber are divided by the above-mentioned respective numbers. By photographing a cross section of fiber bundles constituting a fibrous substrate in this way, it is possible to obtain easily the average fineness of the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B), the number of strands thereof and the ratio between the numbers. The weight ratio between the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B) can also be obtained by selecting any one of solvents which have different solubility or decomposability against the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B) and then removing only the elastic microfibrillar fibers (A) or only the non-elastic microfibrillar fibers (B) from the fibrous substrate. It is easy to know whether or not the fiber length is 5 mm or more by producing a fiber-entangled nonwoven cloth, converting the elastic polymer and the non-elastic polymer to fiber bundles, taking out the bundle and observing it with a microscope. The number of strands of the microfibrillar fibers (A) and (B), referred to in the present invention, is an average value. The ratio between the numbers is a ratio between the average values of the numbers.

[0030] In the present invention, the microfibrillar fibers are preferably composed only of the elastic microfibrillar fibers (A) and the non-elastic microfibrillar fibers (B). However, fibers that do not fall within the scope of the present invention may be incorporated in a small amount so far as the texture and appearance of the present invention are not damaged. One or more various stabilizers and/or coloring agents may be incorporated into the fibers.

[0031] The microfibrillar fiber-forming fibers are opened with a card, passed through a webber to form random webs

or cross-lap webs. The resultant webs are laminated to desired weight and thickness. The laminated webs are then subjected to a known entangling treatment such as needle punching or water-jet entanglement to convert the webs to a nonwoven fabric. Of course, at the time of the conversion to the nonwoven fabric, other microfine fibers, microfine fiber-forming fibers and/or ordinary fibers may be added so far as the object of the present invention is not highly damaged. If necessary, a resin which can be dissolved away, for example, a polyvinyl alcohol-based resin, may be added to the nonwoven fabric to set the same provisionally.

[0032] If necessary, the fiber-entangled nonwoven fabric may be impregnated with a solution or an emulsion of a nonfibrous elastic polymer in a small amount and coagulated for the purpose of adjustment of texture. However, when the amount of the nonfibrous elastic polymer is large, texture like natural leather cannot be obtained. Therefore, the amount is preferably about 10% or less by weight based on the fibrous substrate. Examples of suitable elastic polymers with which the fiber-entangled nonwoven fabric is impregnated include polyurethanes obtained by reacting at least one selected from polymer diols having a number-average molecular weight of 500 to 3500, such as polyester diols, polyether diols, polyether ester diols and polycarbonate diols with at least one diisocyanate selected from aromatic, alicyclic and aliphatic diisocyanates such as 4,4'-diphenylmethane diisocyanate, isophorone diisocyanate or hexamethylene diisocyanate and a low molecular weight compound having two or more active hydrogen atoms, such as ethylene glycol or ethylenediamine at a prescribed molar ratio. Such a polyurethane is used as a polymer composition to which a polymer such as synthetic rubber or polyester elastomer is optionally added. The elastic polymer such as polyurethane is dissolved in a solvent or is dispersed in a non-solvent such as water, and then the fiber-entangled nonwoven fabric is impregnated with the resultant polymer solution. The resultant product is treated with a non-solvent for the polymer to effect wet coagulation, or is heat-treated or treated with hot water to effect dry coagulation or hot water coagulation. Thus, a fibrous substrate is obtained. An additive or additives such as a coloring agent, coagulation regulator or an antioxidant may be added to the polymer solution.

[0033] Next, the fibrous substrate is treated with a liquid which is a non-solvent for the non-elastic polymer, the elastic polymer and the polymer used for the impregnation and which is a solvent or a decomposing agent for the sea component of the microfine fiber-forming fibers. For example, toluene is used when the non-elastic polymer is nylon, polyethylene terephthalate or polypropylene, the elastic polymer is a polyurethane, an ester elastomer or an amide elastomer and the sea component is polyethylene. An aqueous caustic soda solution is used when the non-elastic polymer is nylon, polyethylene terephthalate or polypropylene, the elastic polymer is a polyurethane or an amide elastomer and the sea component is an easily alkali-decomposable polyester. By this treatment, the sea component polymer is removed from the microfine fiber-forming fibers of the present invention so that the fibers are converted to microfine fiber bundles wherein the non-elastic microfine fibers (B) and the elastic microfine fibers (A) are blended and integrated with each other. At the same time, the elastic polymer is swelled with the solvent so that the non-elastic microfine fibers (B) near the elastic microfine fibers (A) are bound. As a result, soft microfine fiber bundles like natural leather are obtained wherein both of the elastic microfine fibers (A) and the non-elastic microfine fibers (B) are divided into microfibers and the microfine fibers gather densely.

[0034] The thus obtained sheet is substantially composed only of the microfine fiber bundles described above. Therefore, the sheet has a fibrous substrate structure like natural leather. As a result, the sheet has texture and appearance like natural leather, which is different from artificial leather in the prior art, and is applicable, as a suede type or a grain-like type, to wide goods such as clothing, furniture, shoes and bags. The sheet of the present invention is especially useful for fields of high-class grain-like goods and high-class suede goods.

[0035] The suede type sheet can be obtained by napping at least one surface of the fibrous substrate, dyeing the suede type fibrous substrate in a normal dyeing manner using a dye made mainly e.g. of an acidic dye, a premetallized dye or a dispersed dye, and optionally subjecting the dyed suede type fibrous substrate to finishing treatment such as rubbing, softening and brushing.

[0036] On the other hand, concerning the grain-like type, a surface coating layer that will be the grain-like face layer is formed as follows: (1) a transcription method of applying a solution or a dispersion solution of an elastic polymer such as polyurethane, to which a coloring agent may be optionally added, to a releasable supporter, and jointing/integrating the supporter with a fiber-entangled nonwoven fabric before the applied coat layer loses adhesiveness, or drying the coat layer and jointing/integrating the dried coat layer with a fiber-entangled nonwoven fabric by means of a soft adhesive agent; (2) a method comprising applying a solution or a dispersion solution of an elastic polymer such as polyurethane directly to a fiber-entangled nonwoven fabric with a gravure roller; or (3) a coating method comprising i) carrying out, for example, a process of applying such a solution or a dispersion solution in a roller coating manner, performing wet coagulation, drying and surface-coloring to form a surface coat layer, and then ii) finishing the layer with embossing. If the surface finishing of the grain-like leather on which the surface coat layer is formed is insufficient, a polyurethane solution containing a coloring agent or no coloring agent is applied to this sheet to adjust color or gloss. The sheet is optionally subjected to finishing treatment such as softening, dyeing treatment or a treatment with a water repellent, and is subsequently subjected to e.g. rubbing or embossing treatment, so as to make a grain-like leather. As described above, any method that is generally used may be used.

[0037] The following will describe embodiments of the present invention by way of working examples. The present invention is not however limited to these examples. Parts and percentage in the examples are by weight unless specified otherwise. The ratio of the swelling of the non-elastic microfine fibers (B) with an extracting solvent was calculated as follows. Components other than the non-elastic microfine fibers (B) were removed from the resultant artificial leather, leaving the non-elastic microfine fibers (B). Thereafter, the non-elastic microfine fibers (B) were vacuum-dried at 50-100°C for 20 hours and then formed into a film 100 µm in thickness at a temperature at which the non-elastic microfine fibers (B) could be thermally melted by means of a press molding machine. The film was cut into squares, each side of which was 10 cm, and then the weight (W0) of the square was measured. Thereafter, the square was immersed in an extracting solvent at an extracting temperature for 1 hour and then the solvent adhering to the surface was wiped out. The weight (W) of the resultant square was measured. The swelling ratio was calculated according to the following calculating equation.

$$\text{The swelling ratio (\% by weight) of the non-elastic microfine fibers (B)} = (W - W0) \times 100 / W0$$

Example 1

[0038] A melt formed by melting 40 parts of nylon-6 [a non-elastic polymer constituting the non-elastic microfine fibers (B)] and 40 parts of polyethylene (melt index = 70) in a single system, and a melt formed by melting 20 parts of a polyester-based polyurethane [an elastic polymer constituting the elastic microfine fibers (A)] in another system were spun in the manner that the number of the islands of the elastic polymer would be 25 by a spinning method of defining the fiber shape at a spinneret portion. Thus, microfine fiber-forming fibers were obtained which had a fineness of 15 deniers, a ratio between the number of strands (A/B) of 1/24, and a weight ratio (A/B) of 33/67. At this time, a cross section of the fibers was observed. As a result, the average number of strands of the non-elastic microfine fibers (B) composed of nylon-6 was about 600. The polyester-based polyurethane and nylon-6 were substantially homogeneously dispersed and the non-elastic microfine fibers (B) composed of nylon-6 encircled each of the polyester-based polyurethane microfine fibers (A). The resultant fibers were stretched by 3.0 times, crimped, cut to a fiber length of 51 mm, opened with a card, and formed into webs with a cross-lap webber. Next, the webs were converted to a fiber-entangled nonwoven fabric having a basic weight of 700 g/cm² with a needle punch. During these steps, the size of the fibers was reduced to about 5.9 deniers. This fiber-entangled nonwoven fabric was impregnated with an aqueous polyurethane emulsion composition containing 3% polyether-based polyurethane (the added amount of the polyurethane: 2% of the fibers after the fibers were made microfine), and then thermally treated. Polyethylene in the microfine fiber-forming fibers was then extracted and removed with toluene at 90°C. The ratio of the swelling of the non-elastic microfine fibers (B) with 90°C-toluene was 1%. The treatment for removing the sea component gave a fibrous substrate of about 1.3 mm in thickness comprising microfine fiber bundles wherein the polyester-based polyurethane microfine fibers (A) and nylon-6 were mixed and integrated with each other, and nonfibrous polyurethane (the content by weight = 2% by weight).

[0039] According to observation of a cross section of the microfine fiber bundle of this fibrous substrate with an electron microscope, the microfine fiber (A) comprising the polyester-based polyurethane was separated into about 25 strands, and the polyester-based polyurethane microfine fibers hardly agglutinated to each other. Moreover, it was found that this fiber had a structure wherein the microfine fiber (A) comprising the polyester-based polyurethane and the microfine fibers (B) were mixed and integrated with each other and they agglutinated partially and that the non-elastic microfine fibers (B) encircled each of the microfine fibers (A). The average fineness of the microfine fiber (A) comprising the polyester-based polyurethane was 0.055 denier and a scattering in the fineness was hardly recognized. The average fineness of the microfine fibers comprising nylon-6 was 0.004 denier. The fiber length of most of the microfine fibers (B) comprising nylon-6 was 5 mm or more. One surface of this substrate was subjected to buffing to adjust its thickness to 1.20 mm. Thereafter, the other surface was subjected to an emery buffing machine to form a microfine fiber-napped surface. The substrate was further dyed with Irgalan Red 2GL (made by Chiba Geigy) having a concentration of 4% owf, and was finished. The resultant suede-like artificial leather was soft and had weak repellence feeling and rubbery feeling. The leather also had drapeability and texture like natural leather, was excellent in color-developability, and exhibited elegant lighting. Its appearance was also very good.

[0040] The above-mentioned fibrous substrate was finished into a grain-like artificial leather in the following manner. As a result, the leather was soft. The leather also had weak repellence feeling and rubbery feeling, and texture like natural leather. Its crease feeling was like natural leather, and its appearance was excellent.

[0041] The manner for finishing into the grain-like artificial leather: one surface of the above-mentioned fibrous substrate was subjected to buffing to adjust its thickness to 1.20 mm. The surface was then brought into contact with a flat roller of 120°C to conduct surface smoothing treatment, and was subsequently coated with a 20% polyurethane solution by means of a gravure roller. Further, the surface was coated with a 10% polyurethane solution by means of the gravure roller. The polyurethane-coated surface was embossed with a heated embossing roller to finish the substrate

into the grain-like artificial leather. The resultant grain-like artificial leather had high-class feeling having texture and appearance like natural leather.

Example 2

[0042] The same operation as in Example 1 was performed except that nylon-6 of the non-elastic polymer was replaced with a copolymer of nylon-6 and nylon-66, to obtain a suede-like artificial leather. The swelling ratio of the non-elastic microfibrillar fibers was 3%. The resultant suede-like artificial leather had texture like natural leather in the same manner as in Example 1. Results from observation with an electron microscope were also the same as in Example 1. Its appearance was also good.

Example 3

[0043] The same operation as in Example 1 was performed except that the polyester-based polyurethane of the elastic polymer and nylon-6 of the non-elastic polymer were replaced with a polyether-based ester elastomer and 10 mol%-isophthalic acid modified polyethylene terephthalate, respectively, and a dispersed dye was used as a dye, to obtain a suede-like artificial leather. The swelling ratio of the non-elastic microfibrillar fibers was 7%. The resultant suede-like artificial leather had texture like natural leather in the same manner as in Example 1. Its appearance was also good.

Comparative Example 1

[0044] The same operation as in Example 1 was performed except that the spinning method of defining the fiber shape at the spinneret portion was replaced with a spinning method of repeating joint/division at a spinning heat portion to form a blend system of the two, and the 25 islands of the elastic polymer were replaced with 10 islands thereof, so as to obtain a suede-like artificial leather. According to observation of a section of the microfibrillar fiber bundle with an electron microscope, it was expected that the number of the islands of the polyester-based polyurethane was 100 but the polyester-based polyurethane fibers adhered and agglutinated to be integrated with each other. The nylon-6 fibers were embraced therein. The resultant suede-like artificial leather was harder, and had more paper-like texture and poorer surface lighting and appearance, as compared with that of Example 1.

Comparative Example 2

[0045] The same operation as in Example 1 was performed except that the melt index of polyethylene was changed from 70 to 120, the number of the islands of nylon-6 was changed from 600 to 100, the number of strands of the polyester-based polyurethane was changed to 40, and the ratio between the numbers of strands was changed from 1/24 to 1/2.5, so as to obtain a suede-like artificial leather. According to observation of a cross section of the microfibrillar fiber bundle with a microscope, it was expected that the ratio of the numbers of strands between the polyester-based polyurethane and nylon-6 was 1/2.5 but the polyester-based polyurethane fibers agglutinated to be integrated with each other. The nylon-6 fibers were embraced therein. Thus, the numbers of strands and the ratio between the numbers of strands were not able to be counted. The resultant suede-like artificial leather was harder, and had more paper-like texture and poorer surface lighting and appearance, as compared with that of Example 1.

Comparative Example 3

[0046] The same operation as in Example 1 was performed except that the weight ratio of the polyester-based polyurethane to nylon-6 was changed from 33/67 to 5/95, so as to obtain a suede-like artificial leather. According to observation of a cross section of the microfibrillar fiber bundle with an electron microscope, the polyester-based polyurethane was microfibrillar but the microfibrillar fibers comprising nylon-6 were hardly bound to the microfibrillar fibers comprising the polyester-based polyurethane. Its structure was loose. The resultant suede-like artificial leather had more paper-like texture than that of Example 1. A great deal of surface nap fell out. Its appearance was poor.

Comparative Example 4

[0047] The same operation as in Example 1 was performed except that the weight ratio of the polyester-based polyurethane to nylon-6 was changed from 33/67 to 80/20, so as to obtain a suede-like artificial leather. According to observation of a cross section of the microfibrillar fiber bundle with an electron microscope, the polyester-based polyurethane fibers agglutinated to be integrated with each other. The nylon-6 fibers were embraced therein. The resultant suede-like artificial leather was harder, and had texture having stronger repellence feeling and rubbery feeling, as compared with

that of Example 1. This leather also had poorer surface lighting and appearance.

Comparative Example 5

- 5 [0048] The same operation as in Example 1 was performed except that the number of the islands of the polyester-based polyurethane was set up to 1 instead of 25, so as to obtain a suede-like artificial leather. According to observation of a cross section of the microfine fiber bundle with an electron microscope, the bundle had a structure wherein one strand of the polyester-based polyurethane fiber having an average fineness of 1.5 denier and the nylon-6 fibers were mixed and integrated with each other. The resultant suede-like artificial leather exhibited texture having stronger repellence feeling than the artificial leather of Example 1, had in its surface white, striking napped markings, and gave rough touch and poor appearance and surface feeling.

Comparative Example 6

- 15 [0049] The same operation as in Example 1 was performed except that the spinning method of defining the fiber shape at the spinneret portion in the manner that the number of the islands of the elastic polymer would be 25 was replaced with a spinning method using a spinneret having a side-by-side type structure, and the 25 islands of the elastic polymer were replaced with a single prejudiced core, so as to obtain a suede-like artificial leather. According to observation of a cross section of the microfine fiber bundle with an electron microscope, pieces of unevenly distributed polyester-based polyurethane adhered to each other and a part of the nylon-6 fibers was embraced therein. The resultant suede-like artificial leather was harder and had more paper-like texture and poorer surface lighting and appearance, as compared with that of Example 1.

Effect of the present invention

- 25 [0050] The fibrous substrate for artificial leather obtained by the present invention has texture and appearance like natural leather. Thus, the substrate is applicable, as a suede type or a grain-like type, to various goods for clothing, furniture, shoes, bags and the like. The fibrous substrate for artificial leather of the present invention is especially useful in the field of high-class grain-like goods and high-class suede-like goods which could have heretofore been obtained from only natural leather.

Claims

- 35 1. A fibrous substrate for artificial leather, comprising microfine fiber bundles, each of which is composed of 3-50 numbers of microfine fibers (A) comprising an elastic polymer and having an average fineness of 0.5 denier or less and 15 or more numbers of microfine fibers (B) comprising a non-elastic polymer and having an average fineness of 0.2 denier or less, the microfine fiber bundles satisfying the following conditions (1)-(3):
- 40 (1) the ratio of the number of strands of the A to the number of strands of the B in cross sections of the bundles (A/B) is 1/5 or less,
 (2) the ratio of the weight of the A to the weight of the B in the bundles (A/B) is 10/90-60/40, and
 (3) the microfine fibers (B) comprising the non-elastic polymer encircle each of the microfine fibers (A) comprising the elastic polymer.
- 45 2. The fibrous substrate for artificial leather according to claim 1, wherein the ratio of the fineness of the microfine fibers (A) to that of the microfine fibers (B) (A/B) ranges from 2 to 5000.
3. The fibrous substrate for artificial leather according to claim 1 or 2, wherein the elastic polymer is a polyurethane.
- 50 4. The fibrous substrate for artificial leather according to any one of claims 1 to 3 wherein the non-elastic polymer is at least one polymer selected from polyamides, polyesters and polyolefines.
- 55 5. The fibrous substrate for artificial leather according to any one of claims 1 to 4, wherein the fibrous substrate is impregnated with the elastic polymer in an amount of 10% or less by weight of the microfine fibers constituting the substrate.
6. A suede-like artificial leather obtainable by napping at least one surface of the substrate according to any one of claims 1 to 5.

7. An artificial leather, having a grain-like face layer, obtainable by coating at least one surface of the substrate according to any one of claims 1 to 5 with a resin layer.

5

10

15

20

25

30

35

40

45

50

55

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 067 234 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
02.01.2004 Bulletin 2004/01

(51) Int Cl.7: **D06N 3/00**

(43) Date of publication A2:
10.01.2001 Bulletin 2001/02

(21) Application number: 00114045.8

(22) Date of filing: 05.07.2000

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 05.07.1999 JP 19023499

(71) Applicant: **KURARAY CO., LTD.**
Kurashiki-shi, Okayama-ken 710 (JP)

(72) Inventors:
• **Nakayama, Kimio**
Kurashiki-shi, Okayama-ken (JP)
• **Yamasaki, Tsuyoshi**
Kurashiki-shi, Okayama-ken (JP)
• **Tamba, Yoshihiro**
Kurashiki-shi, Okayama-ken (JP)

(74) Representative: **VOSSIUS & PARTNER**
Siebertstrasse 4
81675 München (DE)

(54) Fibrous substrate for artificial leather and artificial leather using the same

(57) A fibrous substrate for artificial leather, comprising microfine fiber bundles, each of which is composed of 3-50 microfine fibers (A) comprising an elastic polymer and having an average fineness of 0.5 denier or less and 15 or more microfine fibers (B) comprising a non-elastic polymer and having an average fineness of 0.2 denier or less, the microfine fiber bundles satisfying the following conditions (1)-(3):

- (1) the ratio of the number of strands of the A to the number of strands of the B in cross sections of the bundles (A/B) is 1/5 or less,
- (2) the ratio of the weight of the A to the weight of

the B in the bundles (A/B) is 10/90-60/40, and
(3) the microfine fibers (B) comprising the non-elastic polymer encircle each of the microfine fibers (A) comprising the elastic polymer.

It is possible to obtain, from the fibrous substrate, suede-like artificial leather and grain-like artificial leather having texture and appearance like natural leather, and having high-class feeling never available from artificial leather in the prior art.

EP 1 067 234 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 11 4045

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 651 090 A (KURARAY CO) 3 May 1995 (1995-05-03)	6	D06N3/00
A	* comparative example 3 * * claims *	1-5,7	
D,X	--- DATABASE WPI Section Ch, Week 199404 Derwent Publications Ltd., London, GB; Class F04, AN 1994-032266 XP002259129 & JP 05 339863 A (KURARAY CO LTD), 21 December 1993 (1993-12-21)	6	
A	* abstract *	1-5	
X	--- DATABASE WPI Section Ch, Week 199524 Derwent Publications Ltd., London, GB; Class A82, AN 1995-183410 XP002259132 & JP 07 102488 A (KURARAY CO LTD), 18 April 1995 (1995-04-18)	7	TECHNICAL FIELDS SEARCHED (Int.Cl.7) D06N D04H
	* abstract *		
X	--- DATABASE WPI Section Ch, Week 199233 Derwent Publications Ltd., London, GB; Class A28, AN 1992-273014 XP002259133 & JP 04 185777 A (KURARAY CO LTD), 2 July 1992 (1992-07-02)	7	
A	* abstract *		
A	--- US 4 515 854 A (KOGAME KUNIO ET AL) 7 May 1985 (1985-05-07) * column 9, line 47 - line 54; claims *	1-7	
D	& JP 59 211664 A (...) 30 November 1984 (1984-11-30) --- -/--		
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 24 October 2003	Examiner Pamies Olle, S
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 03 02 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 11 4045

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 4 833 012 A (MAKIMURA MASARU ET AL) 23 May 1989 (1989-05-23) * column 5, line 50 - line 58; claims *	1-7	
D	& JP 63 012744 A (...) 20 January 1988 (1988-01-20) ---		
D,A	DATABASE WPI Section Ch, Week 198516 Derwent Publications Ltd., London, GB; Class A94, AN 1985-096719 XP002259130 & JP 60 045656 A (TORAY IND INC), 12 March 1985 (1985-03-12) * abstract * -----	1-7	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 24 October 2003	Examiner Pamies 011e, S
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document		T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document	

EPO FORM 1503 (03.02) (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 4045

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-10-2003

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 0651090	A	03-05-1995	CN	1116669 A ,B	14-02-1996
			DE	69424918 D1	20-07-2000
			DE	69424918 T2	12-10-2000
			EP	0651090 A1	03-05-1995
			JP	3109793 B2	20-11-2000
			JP	7173778 A	11-07-1995
			KR	180949 B1	01-04-1999
			US	5503899 A	02-04-1996

JP 5339863	A	21-12-1993	JP	3103434 B2	30-10-2000

JP 7102488	A	18-04-1995	JP	3142098 B2	07-03-2001

JP 4185777	A	02-07-1992	JP	3043049 B2	22-05-2000

US 4515854	A	07-05-1985	JP	1041742 B	07-09-1989
			JP	1580574 C	11-10-1990
			JP	59211666 A	30-11-1984
			JP	59211664 A	30-11-1984
			DE	3485397 D1	13-02-1992
			EP	0125494 A2	21-11-1984

US 4833012	A	23-05-1989	JP	2027811 C	26-02-1996
			JP	7062302 B	05-07-1995
			JP	63012744 A	20-01-1988
			DE	3778221 D1	21-05-1992
			EP	0251183 A2	07-01-1988

JP 60045656	A	12-03-1985	JP	1642463 C	28-02-1992
			JP	2053540 B	19-11-1990

EPO FORM P0453

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record.**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.